

TECHNICAL DATA SHEET (TDS)

## P88 MAX MULTI PURPOSE PU FOAM

### 1 – DESCRIPTION

**Demsun P88 MAX** is a low expansion and maximum yield formulation aerosol polyurethane foam especially developed for fixing door&window frames. It yields minimum %100 more foam than straw foams, cures faster and forms easy to cut flexible foam

### 2 – PROPERTIES

- Maximum Yield: Provides %100 more yield than that of standard straw foams.
- Low-Expansion: Ensures not to bend or bow door and window frames. Decreases foam waste.
- Fast Cure: Becomes tack free in 5 minutes and cut able within 45 minutes.
- Cures Flexible: Easier to cut if the gap is overfilled
- Reusable: Highest technology valves system provides none sticking and reusability.
- Improved Adhesion&Stability: Better non-sagging performance on vertical surfaces.
- Usable in 4 Seasons: Special formulation allows application at low temperatures (-5 °C)
- Polyurethane based: Perfect adhesion on common building materials.
- Closed-Cell Structure: Provides effective heat&sound insulation.
- It does not contain any propellant gases which are harmful to the ozone layer.

### 3 - APPLICATIONS

- Fixing and insulating of door and window frames.
- Filling and sealing gaps, joints and cavities.
- Filling of penetrations in walls.
- Insulating electrical outlets and water pipes.

### 4 - INSTRUCTIONS

Optimal can temperature is +20 °C. Application (ambient) temperature is between +5 °C to +30 °C. Shake the can well before use. Screw the adapter on the valve. Hold the can upside down and activate the foam by pressing the valve. Moisturizing the surfaces and the foam improves adhesion and shortens curing time. Fresh foam can be cleaned by Demsun C80 Foam Cleaner. Cured foam can be cleaned barely mechanically.

### 5- PACKAGING

Product	Volume	Package
P88 MAX	850ml/1000gr	12

### 6- STORAGE AND SHELF LIFE

15 months if stored properly.

### 7- RESTRICTIONS

- Storage above +25 °C and below +5 °C shortens shelf life.

## TECHNICAL DATA SHEET (TDS)

- Should be stored and transported in vertical position.
- Should be kept in room temperature for at least 12 hours before the application.
- Cured foam will discolor if exposed to ultraviolet light.
- Paint or coat the cured foam for best results in outdoor applications.
- Lower temperatures decreases yield and curing time.

### 8- SAFETY

Contains Diphenylmethane-4,4'-Diisocyanate. Harmful by inhalation. Irritating to eyes, respiratory system and skin. Do not breathe spray/vapour. Wear suitable protective clothing and gloves. Use only in well-ventilated areas. Pressurized container. Keep away from direct sunlight and do not expose temperatures over 50 °C. Do not pierce or burn, even after use. Keep away from sources of ignition, no smoking. Keep out of the reach of children.

### 9- TECHNICAL PROPERTIES

<b>Basis</b>	: Polyurethane Prepolymer	
<b>Curing System</b>	: Moisture cure	
<b>Specific Gravity</b>	: 22±3 Kg/cm <sup>3</sup>	(ASTM D1622)
<b>Tack-Free Time (1 cm width)</b>	: 7±3 min	(ASTM C1620)
<b>Cutting Time (1cm width)</b>	: 30-45 min	(ASTM C1620)
<b>Cure-Time</b>	: 24 hours	
<b>Foam Colour</b>	: Light yellow	
<b>Yield</b>	: 30-45 L	(ASTM C1536)
<b>Fire Class of the Cured Foam</b>	: B3	(DIN 4102-1)
<b>Thermal Conductivity</b>	: 0,036 W/m.k (at 20°C)	(DIN 52612)
<b>Compression Strength</b>	: 0,03 MPa	(DIN 53421)
<b>Tensile strength</b>	: 11.7±0.8	(SO1926-79)
<b>Dimensional stability</b>	: ±10%	(ISO2796/86)
<b>Water penetration</b>	: 0	(ISO2896-87)
<b>Water Absorption</b>	: max. 1 vol%	(DIN 53428)
<b>Can Temperature</b>	: min.5°C max. +30°C	
<b>Temperature Resistance</b>	: -40°C to +80°C	
<b>Application Temperature</b>	: +5°C to +30°C	